



2FM4.5 (4V4.5Ah)




2FM4.5 is a general purpose battery with 5 years life in standby service, or more than 260 cycles at 100% D.O.D by cyclic use. As with all QiangJun batteries, all FM models are rechargeable, highly efficient, leak proof and maintenance free.

Cells Per Unit	2
Voltage Per Unit	4
Capacity	4.5Ah@ 20hr-rate to 1.75V per cell @ 25°C
Weight Max. Discharge C	Approx. 0.5 Kg
urrent Internal Resistan	45 A (5 sec)
ce	Approx. 12 mm
Operating Temperature Range	Discharge: -20°C ~60°C Charge: 0°C~50°C St orage: -20°C~60°C
Normal Operating Temperature Range	25°C±5°C
Float charging Voltage	4.5 to 4.6 VDC/unit Average at 25°C
Recommended Maximum Charging Current Limit	1.35 A
Equalization and Cycle Service	4.8 to 5.0 VDC/unit Average at 25°C
Self Discharge	QiangJun batteries can be stored for more than 6 month at 25°C. Please charge batteries before using. For higher temperature, the time interval will be shorter.
Terminal	Faston Tab 187(F1)
Constainer Material	A.B.S. (UL94-HB) Flammability resistance of UL94-V2 can be available upon request.



Dimensions



Constant Current Discharge Characteristics Unit: A(25°C)

F.V/Time	5MIN	10MIN	15MIN		1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	18.7	12.5	9.60	5.28	3.12	1.87	1.15	0.95	0.76	0.56	0.44	0.25
1.67V	17.5	11.7	9.02	5.20	3.11	1.86	1.15	0.94	0.76	0.56	0.44	0.24
1.70V	16.5	11.3	8.82	5.16	3.08	1.85	1.14	0.94	0.75	0.56	0.43	0.23
1.75V	14.9	10.6	8.36	5.04	3.04	1.83	1.14	0.93	0.75	0.56	0.43	0.23
1.80V	13.3	9.85	7.89	4.92	2.99	1.80	1.13	0.93	0.74	0.55	0.42	0.22
1.85V	11.8	9.12	7.43	4.80	2.95	1.77	1.12	0.92	0.74	0.55	0.41	0.21

Constant Power Discharge Characteristics Unit: W(25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	36.0	23.4	19.0	10.6	6.24	3.74	2.30	1.88	1.79	1.12	0.88	0.49
1.67V	33.8	22.5	18.0	10.4	6.22	3.72	2.30	1.88	1.77	1.12	0.87	0.47
1.70V	33.1	21.8	17.6	10.3	6.21	3.71	2.29	1.88	1.77	1.11	0.86	0.46
1.75V	29.9	20.9	16.7	10.1	6.11	3.65	2.28	1.86	1.76	1.11	0.85	0.45
1.80V	26.7	19.6	15.8	9.83	6.00	3.60	2.26	1.85	1.76	1.10	0.84	0.43
1.85V	23.5	18.2	14.9	9.59	5.90	3.55	2.24	1.84	1.76	1.10	0.82	0.42


All mentioned values are average values.

2FM4.5


4V4.5Ah




Temperature effects curve




Storage characteristic




Life characteristics of cyclic use




Effect of Temperature on long term float life



Charge characteristic curve for standby use



Discharge characteristic curve



Charging Procedures

Application	Charge Voltage (V)			Max. Charge Current
	Temperature	Set point	Allowable range	
Cycle Use	25°C	14.7	14.4~15.0	0.3C
Standby	25°C	13.7	13.6~13.8	0.3C

Discharge Current VS. Discharge Voltage

Final Discharge Voltage V/cell	1.75V	1.70V	1.60V
Discharge Current (A)	A 0.2C	0.2C < (A) <	(A) ≥ 1.0C

Charge the batteries at least once every six months, if they are stored at 25°C.

Charging Method:

Constant Voltage	14.4~15.0V, 5~11h, Max. Current 0.1CA
Constant Current	0.1CA x 5h
Fast	0.3CA x 1.7h

Charging Procedures(4V series)

Application	Charge Voltage (V)			Max. Charge Current
	Temperature	Set point	Allowable range	
Cycle Use	25°C	4.9	4.8~5.0	0.3C
Standby	25°C	4.55	4.5~4.6	0.3C

QIANGJING BATTERY CO.,LTD
 Mudan Road Xiacheng Town,
 Yueyang District,
 Xiangtan City, Hunan P.R.China