



# 3FM6 (6V6.0Ah)

3FM6 is a general purpose battery with 5 years life in standby service, or more than 260 cycles at 100% D.O.D by cyclic use. As with all QiangJun batteries, all FM models are rechargeable, high efficient, leak proof and maintenance free.




## Specification

Cells Per Unit	3
Voltage Per Unit	6
Capacity	6.0Ah@ 20hr-rate to 1.75V per cell @ 25°C
Weight	Approx. 0.9 Kg
Max. Discharge Current	60 A (5 sec)
Internal Resistance	Approx. 18 m
Operating Temperature Range	Discharge: -20°C~60°C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C±5°C
Float charging Voltage	6.8 to 6.9 VDC/unit Average at 25°C
Recommended Maximum Charging Current Limit	1.8 A
Equalization and Cycle Service	7.25 to 7.45 VDC/unit Average at 25°C
Self Discharge	QiangJun batteries can be stored for more than 6 months at 25°C. Please charge batteries before using. For higher temperature, the time interval will be shorter
Terminal	Faston Tab 187(F1)
Container Material	A.B.S. (UL94-HB) Flammability resistance of UL94-V2 can be available upon request.



## Dimensions



### Constant Current Discharge Characteristics Unit: A(25°C)

F.V/Time	5MIN	10MIN	15MIN		1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	24.9	16.7	12.8	7.04	4.16	2.50	1.54	1.26	1.01	0.74	0.59	0.33
1.67V	23.3	15.5	12.0	6.93	4.14	2.48	1.53	1.25	1.01	0.74	0.58	0.32
1.70V	22.1	15.1	11.8	6.88	4.11	2.47	1.52	1.25	1.00	0.74	0.58	0.31
1.75V	19.9	14.1	11.1	6.72	4.05	2.44	1.52	1.24	1.00	0.74	0.57	0.30
1.80V	17.8	13.1	10.5	6.56	3.99	2.40	1.51	1.24	0.99	0.74	0.56	0.29
1.85V	15.7	12.2	9.91	6.40	3.94	2.36	1.49	1.23	0.98	0.74	0.55	0.28

### Constant Power Discharge Characteristics Unit: W(25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	48.0	31.2	25.4	14.1	8.32	4.99	3.07	2.51	2.38	1.49	1.17	0.65
1.67V	45.0	30.0	24.1	13.8	8.30	4.96	3.06	2.50	2.36	1.49	1.16	0.63
1.70V	44.1	29.1	23.5	13.8	8.28	4.94	3.05	2.50	2.36	1.48	1.15	0.62
1.75V	39.9	27.9	22.3	13.4	8.14	4.87	3.04	2.48	2.35	1.48	1.13	0.59
1.80V	35.6	26.1	21.0	13.1	8.00	4.80	3.01	2.47	2.35	1.47	1.12	0.58
1.85V	31.4	24.3	19.8	12.8	7.87	4.73	2.99	2.45	2.34	1.47	1.10	0.56


All mentioned values are average values.

# 3FM6


6V6.0Ah




## Temperature effects curve




## Storage characteristic




## Life characteristics of cyclic use




## Effect of Temperature on long term float life



## Charge characteristic curve for standby use



## Discharge characteristic curve



## Charging Procedures

Application	Charge Voltage (V)			Max. Charge Current
	Temperature	Set point	Allowable range	
Cycle Use	25°C	14.7	14.4~15.0	0.3C
Standby	25°C	13.7	13.6~13.8	0.3C

## Discharge Current VS. Discharge Voltage

Final Discharge Voltage V/cell	1.75V	1.70V	1.60V
Discharge Current (A)	(A) ≤ 0.2C	0.2C < (A) <	(A) ≥ 1.0C

Charge the batteries at least once every six months, if they are stored at 25°C.

## Charging Method:

Constant Voltage	7.25~7.45V, 5~11h, Max. Current 0.1CA
Constant Current	0.1CA × 5h
Fast	0.3CA × 1.7h

## Charging Procedures (6V series)

Application	Charge Voltage (V)			Max. Charge Current
	Temperature	Set point	Allowable range	
Cycle Use	25°C	7.35	7.25~7.45	0.3C
Standby	25°C	6.85	6.8~6.9	0.3C

**QIANGJING BATTERY CO.,LTD**  
 Mudan Road Xiacheng Town,  
 Yuefang District,  
 Xiangtan City, Hunan P.R.China